



Europäisches  
Patentamt

European  
Patent Office

Office européen  
des brevets

REC'D 03 NOV 2003

WIPO

PCT

Bescheinigung

Certificate

Attestation

Die angehefteten Unterla-  
gen stimmen mit der  
ursprünglich eingereichten  
Fassung der auf dem näch-  
sten Blatt bezeichneten  
europäischen Patentanmel-  
dung überein.

The attached documents  
are exact copies of the  
European patent application  
described on the following  
page, as originally filed.

Les documents fixés à  
cette attestation sont  
conformes à la version  
initialement déposée de  
la demande de brevet  
européen spécifiée à la  
page suivante.

Patentanmeldung Nr. Patent application No. Demande de brevet n°

02405864.6

**PRIORITY DOCUMENT**  
SUBMITTED OR TRANSMITTED IN  
COMPLIANCE WITH  
RULE 17.1(a) OR (b)

Der Präsident des Europäischen Patentamts;  
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets  
p.o.

R C van Dijk

BEST AVAILABLE COPY



Anmeldung Nr:  
Application no.: 02405864.6  
Demande no:

Anmeldetag:  
Date of filing: 07.10.02  
Date de dépôt:

Anmelder/Applicant(s)/Demandeur(s):

Ciba Specialty Chemicals Holding Inc.  
Klybeckstrasse 141  
4057 Basel  
SUISSE

Bezeichnung der Erfindung/Title of the invention/Titre de l'invention:  
(Falls die Bezeichnung der Erfindung nicht angegeben ist, siehe Beschreibung.  
If no title is shown please refer to the description.  
Si aucun titre n'est indiqué se référer à la description.)

Graftable stabilizers for vulcanizates

In Anspruch genommene Priorität(en) / Priority(ies) claimed / Priorité(s)  
revendiquée(s)

Staat/Tag/Aktenzeichen/State/Date/File no./Pays/Date/Numéro de dépôt:

Internationale Patentklassifikation/International Patent Classification/  
Classification internationale des brevets:

C08K5/00

Am Anmeldetag benannte Vertragsstaaten/Contracting states designated at date of  
filing/Etats contractants désignées lors du dépôt:

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR IE IT LI LU MC NL PT SE SK TR

Graftable stabilizers for vulcanizates

The present invention relates to novel stabilizers of the 4-amino-3-sulfinyl-diphenylamine type, to compositions comprising an elastomer susceptible to oxidative, thermal, dynamic, or light- and/or ozone-induced degradation and, as stabilizer, at least one compound of the 4-amino-3-sulfinyl-diphenylamine type, to the use of the stabilizers to prevent discoloration of a substrate coming into contact with elastomers, and as antiozonants for elastomers to prevent oxidative, thermal, dynamic, or light- and/or ozone-induced degradation, and also to the corresponding processes, and to a process for grafting the stabilizing onto elastomers.


Elastomers such as rubber products (vulcanizates), like all polymers, are susceptible to oxidative, thermal, dynamic or light-induced degradation. A particular factor causing damage to diene rubber vulcanizates is ozone. Ozone attacks the carbon-carbon double bonds, of which many remain in the rubber (vulcanizate), and, via the mechanism known as ozonolysis, causes damage which is apparent as typical surface cracking, and failure of the rubber product. The damage is particularly serious when the rubber product is under dynamic stress.

To prevent ozone damage, antioxidants selected from the class consisting of para-phenylenediamines [see Russel A. Mazzeo et al., "Tire Technology International" 1994, pp. 36 - 46; or Donald E. Miller et al., Rubber World, 200 (5), 13-23 (1989)] are generally added to vulcanizates. These compounds have very good protective action, especially under dynamic conditions, but develop a strong intrinsic colour (discolouring) and, as a result of high migration rate, these compounds give severe contact discoloration (staining), i.e. the dye transfers to other substrates/products on direct contact. This means that the stabilizers employed in the prior art cannot be used as stabilizers for rubber products which are free from carbon black or are "non-black", and they are also unsuitable for (black) rubber products which comprise carbon black and are intended for use in direct contact with pale-coloured products.

There continues to be a need for stabilizers which, although they may have an intrinsic colour, are unable, for example as a result of chemical bonding to the rubber chains, to transfer the colour to other products.

It has now been found that compounds of the 4-amino-3-sulfinyl-diphenylamine type are particularly suitable as stabilizers for elastomers susceptible to oxidative, thermal, dynamic, or light- and/or ozone-induced degradation.

The present invention therefore provides compounds of the formula I



wherein

$R_1$  is  $C_1$ - $C_{18}$ alkyl,  $C_5$ - $C_{12}$ -cycloalkyl, phenyl, benzyl, or allyl;

$n$  is 1 or 2;

if  $n$  is 1,  $R_2$  is  $C_4$ - $C_{18}$ alkyl,  $C_5$ - $C_{12}$ -cycloalkyl, aryl or heteroaryl, benzyl, allyl,  $(CH_2)_mCOOR_3$ , or is  $(CH_2)_mCN$ ;

if  $n$  is 2,  $R_2$  is  $-S-(CH_2)_p-S$  or  $-S-(CH_2)_2-[O-(CH_2)_2]_m-S-$

$R_3$  is  $C_1$ - $C_{18}$ alkyl, benzyl, allyl;

$m$  is 1 or 2; and

$p$  is a number from 2 to 12.

Preferred compound of formula I are those wherein

$R_1$  is  $C_2$ - $C_8$ alkyl, cyclohexyl, phenyl, benzyl, or allyl; especially 2-propyl,  $CH(CH_3)-CH_2-CH(CH_3)_2$ ,  $CH(CH_3)-CH(CH_3)_2$ , 2-octyl, cyclohexyl;

if  $n$  is 1,  $R_2$  is  $C_4$ - $C_{16}$ alkyl, cyclohexyl, phenyl,  $(CH_2)_2COOR_3$ , or is  $(CH_2)_2CN$ ;

if  $n$  is 2,  $R_2$  is  $-S-(CH_2)_p-S-$  with  $p$  ranging from 2 to 6, or is  $-S-(CH_2)_2-O-(CH_2)_2-S-$ ;

especially those wherein  $n$  is 1 and  $R_2$  is alkyl, cyclohexyl,  $(CH_2)_2COOR_3$  or  $(CH_2)_2CN$ ,

most preferred  $R_2$  being  $n$ -octyl,  $t$ -nonyl,  $n$ -dodecyl,  $t$ -dodecyl; and

$R_3$  being  $C_1$ - $C_{18}$ alkyl, especially  $i$ -octyl,  $i$ -tridecyl,  $n$ -dodecyl, stearyl.


Alkyl having up to 18 carbon atoms is a branched or unbranched radical, such as methyl, ethyl, propyl, isopropyl, n-butyl, sec-butyl, isobutyl, tert-butyl, 2-ethylbutyl, n-pentyl, isopentyl, 1-methylpentyl, 1,3-dimethylbutyl, n-hexyl, 1-methylhexyl, n-heptyl, isoheptyl, 1,1,3,3-tetramethylbutyl, 1-methylheptyl, 3-methylheptyl, n-octyl, 2-ethylhexyl, 1,1,3-trimethylhexyl, 1,1,3,3-tetramethylpentyl, nonyl, decyl, undecyl, 1-methylundecyl, dodecyl, 1,1,3,3,5,5-hexamethylhexyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, octadecyl. One of the preferred meanings of  $R_2$  is  $C_4$ - $C_{18}$ alkyl, in particular  $C_8$ - $C_{12}$ alkyl, e.g.  $C_8$ - $C_{12}$ alkyl.


Aryl or heteroaryl are preferably phenyl, naphthyl or pyridyl, especially phenyl.

Tert-butyl stands for 1,1-dimethylethyl; longer alkyl residues denoted as tert.- or t- alkyl such as t-nonyl or t-dodecyl stand for technical isomer mixtures of tertiary alkyl groups  $-C(RR'R'')$  wherein each of R, R' and R'' is alkyl, the total carbon number being as indicated.


Residues i-octyl or i-tridecyl are technical isomer mixtures of primary alkyl groups (commercially available e.g. from Phillips Petroleum).

Examples for compounds of the formula I are:






Compounds of the formula I may, for example, be obtained by known methods, for example, from the corresponding thioethers of formula II



where  $n$ ,  $R_1$  and  $R_2$  are as defined for formula (I), by oxidation, usually with an organic or anorganic peroxide or peracid. Examples are  $H_2O_2$ ,  $H_2O_2$ -urea adduct, t-butylhydroperoxide, cumylhydroperoxide, performic acid, peracetic acid (or a combination of  $H_2O_2$ /acetic acid), trichloro-peracetic acid, m-Chloroperbenzoic acid. Reactions are preferentially carried out in an organic solvent, preferably a polar solvent such as alcohol, ether, a ketone or mixtures thereof. Examples for suitable solvents are ethanol, 2-propanol, (poly)ethylene glycol, (poly)ethylene glycol ethers, acetone, methyl-ethyl-ketone, methyl-isobutyl-ketone. Temperature is usually between  $-5$  and  $+80^\circ C$ , and preferentially ranges from  $35$  to  $50^\circ C$ . The amount of oxidant can be substoichiometric, stoichiometric or an excess. An excess of the oxidant can be destroyed by an appropriate method, e.g. washing with water or an organic or inorganic reducing agent such as sodium pyrosulfate. Further purification of the crude sulfoxide, e.g. with flash chromatography, is optional.

Some of the compounds of the formula II are known from WO 02/42262; others may be obtained in analogous manner by reacting the appropriate quinone diimine and thiol. Thus educt thioethers are obtained by reacting a quinone diimine of formula III




with a thiol of the formula IV



where  $n$ ,  $R_1$  and  $R_2$  are as defined for formula (I).

Reaction conditions often are similar to those described above for the oxidation step with presence of an organic solvent and temperatures conveniently within the range  $-5$  to about  $100^\circ C$ .

The invention also provides some novel thioethers of formula II'



wherein n is 1 or 2,

R<sub>1</sub> is as defined for formula I and

R<sub>2</sub>, if n is 1, is t-nonyl or t-dodecyl or (CH<sub>2</sub>)<sub>2</sub>COOR<sub>3</sub> or (CH<sub>2</sub>)<sub>2</sub>CN, where R<sub>3</sub> is C<sub>1</sub>-C<sub>18</sub>alkyl, especially i-octyl, i-tridecyl, n-dodecyl, stearyl; or

R<sub>2</sub>, if n is 2, is -S-(CH<sub>2</sub>)<sub>p</sub>-S- with p ranging from 2 to 6,

which are useful as intermediates for the synthesis of novel compounds of the formula I.

Preferred compounds of the formula II' are those wherein

n is 1 or 2, especially 1,

R<sub>1</sub> is 2-propyl, -CH(CH<sub>3</sub>)-CH<sub>2</sub>-CH(CH<sub>3</sub>)<sub>2</sub>, -CH(CH<sub>3</sub>)-CH(CH<sub>3</sub>)<sub>2</sub>, 2-octyl or cyclohexyl, especially 2-propyl, and

R<sub>2</sub>, if n is 1, is t-nonyl or t-dodecyl or (CH<sub>2</sub>)<sub>2</sub>COOR<sub>3</sub>, where R<sub>3</sub> is branched C<sub>4</sub>-C<sub>18</sub>alkyl, especially i-octyl, i-tridecyl; or

R<sub>2</sub>, if n is 2, is -S-(CH<sub>2</sub>)<sub>p</sub>-S- with p ranging from 2 to 6.

Some compounds of formula II' of particular technical interest are those wherein n is 1 and

- R<sub>1</sub> is -CH(CH<sub>3</sub>)-CH<sub>2</sub>-CH(CH<sub>3</sub>)<sub>2</sub> and R<sub>2</sub> is t-dodecyl;
- R<sub>1</sub> is -CH(CH<sub>3</sub>)-CH<sub>2</sub>-CH(CH<sub>3</sub>)<sub>2</sub> and R<sub>2</sub> is CH<sub>2</sub>CH<sub>2</sub>COO-i-octyl;
- R<sub>1</sub> is -CH(CH<sub>3</sub>)-CH<sub>2</sub>-CH(CH<sub>3</sub>)<sub>2</sub> and R<sub>2</sub> is t-nonyl;
- R<sub>1</sub> is 2-propyl and R<sub>2</sub> is t-dodecyl;
- R<sub>1</sub> is 2-propyl and R<sub>2</sub> is t-nonyl.

Component b) is suitable for stabilizing elastomers, in particular pale-coloured elastomers, to prevent oxidative, thermal, dynamic, or light- and/or ozone-induced degradation.

Elastomers are to be understood as meaning macromolecular materials which after considerable deformation under a small load at room temperature rapidly regain approximately their original shape. See also Hans-Georg Elias, "An Introduction to Polymer



Science", Section 12. "Elastomers", pp. 388-393, 1997, VCH Verlagsgesellschaft mbH, Weinheim, Germany or "Ullmann's Encyclopedia of Industrial Chemistry, fifth, completely revised edition, Volume A 23", pp. 221-440 (1993).

Examples of elastomers which may be present in the compositions of the invention are the following materials:

1. Polymers of diolefins, for example polybutadiene or polyisoprene.
2. Copolymers of mono- and diolefins with one another or with other vinyl monomers, e.g. propylene-isobutylene copolymers, propylene-butadiene copolymers, isobutylene-isoprene copolymers, ethylene-alkyl acrylate copolymers, ethylene-alkyl methacrylate copolymers, ethylene-vinyl acetate copolymers, acrylonitrile-butadiene copolymers, and also terpolymers of ethylene with propylene and with a diene, such as hexadiene, dicyclopentadiene or ethylidenenorbornene.
3. Copolymers of styrene or  $\alpha$ -methylstyrene with dienes or with acrylic derivatives, e.g. styrene-butadiene, styrene-butadiene-alkyl acrylate and styrene-butadiene-alkyl methacrylate; block copolymers of styrene, e.g. styrene-butadiene-styrene, styrene-isoprene-styrene and styrene-ethylenebutylene-styrene, and also adhesives prepared from the latter three.
4. Halogen-containing polymers, e.g. polychloroprene, chlorinated rubber, chlorinated or brominated copolymer of isobutylene-isoprene (halobutyl rubber).
5. Natural rubber.
6. Aqueous emulsions of natural or synthetic rubbers, e.g. natural rubber latex or latices of carboxylated styrene-butadiene copolymers.

The elastomers to be protected are preferably vulcanized elastomers. Of particular interest are natural rubber and synthetic rubber, and vulcanizates prepared therefrom. Particular preference is given to polydiene vulcanizates, halogen-containing polydiene vulcanizates,

polydiene copolymer vulcanizates, in particular styrene-butadiene copolymer vulcanizates, and ethylene-propylene terpolymer vulcanizates.

Component b) is usefully added to the elastomer to be stabilized in amounts of from 0.05 to 10%, for example from 0.1 to 5%, preferably from 0.5 to 3.0%, based on the weight of the elastomer to be stabilized.

In addition to components a) and b), the compositions of the invention may comprise other additives, such as the following:

### 1. Antioxidants

1.1. Alkylated monophenols, for example 2,6-di-tert-butyl-4-methylphenol, 2-tert-butyl-4,6-dimethylphenol, 2,6-di-tert-butyl-4-ethylphenol, 2,6-di-tert-butyl-4-n-butylphenol, 2,6-di-tert-butyl-4-isobutylphenol, 2,6-dicyclopentyl-4-methylphenol, 2-( $\alpha$ -methylcyclohexyl)-4,6-dimethylphenol, 2,6-dioctadecyl-4-methylphenol, 2,4,6-tricyclohexylphenol, 2,6-di-tert-butyl-4-methoxymethylphenol, nonylphenols which are linear or branched in the side chains, for example 2,6-di-nonyl-4-methylphenol, 2,4-dimethyl-6-(1'-methylundec-1'-yl)phenol, 2,4-dimethyl-6-(1'-methylheptadec-1'-yl)phenol, 2,4-dimethyl-6-(1'-methyltridec-1'-yl)phenol and mixtures thereof.

1.2. Alkylthiomethylphenols, for example 2,4-dioctylthiomethyl-6-tert-butylphenol, 2,4-dioctylthiomethyl-6-methylphenol, 2,4-dioctylthiomethyl-6-ethylphenol, 2,6-di-dodecylthiomethyl-4-nonylphenol.

1.3. Hydroquinones and alkylated hydroquinones, for example 2,6-di-tert-butyl-4-methoxyphenol, 2,5-di-tert-butylhydroquinone, 2,5-di-tert-amylhydroquinone, 2,6-diphenyl-4-octadecyloxyphenol, 2,6-di-tert-butylhydroquinone, 2,5-di-tert-butyl-4-hydroxyanisole, 3,5-di-tert-butyl-4-hydroxyanisole, 3,5-di-tert-butyl-4-hydroxyphenyl stearate, bis(3,5-di-tert-butyl-4-hydroxyphenyl) adipate.

1.4. Tocopherols, for example  $\alpha$ -tocopherol,  $\beta$ -tocopherol,  $\gamma$ -tocopherol,  $\delta$ -tocopherol and mixtures thereof (vitamin E).

1.5. Hydroxylated thiodiphenyl ethers, for example 2,2'-thiobis(6-tert-butyl-4-methylphenol), 2,2'-thiobis(4-octylphenol), 4,4'-thiobis(6-tert-butyl-3-methylphenol), 4,4'-thiobis(6-tert-butyl-2-methylphenol), 4,4'-thiobis(3,6-di-sec-amylphenol), 4,4'-bis(2,6-dimethyl-4-hydroxyphenyl)-disulfide.

1.6. Alkylidenebisphenols, for example 2,2'-methylenebis(6-tert-butyl-4-methylphenol), 2,2'-methylenebis(6-tert-butyl-4-ethylphenol), 2,2'-methylenebis[4-methyl-6-( $\alpha$ -methylcyclohexyl)-phenol], 2,2'-methylenebis(4-methyl-6-cyclohexylphenol), 2,2'-methylenebis(6-nonyl-4-methylphenol), 2,2'-methylenebis(4,6-di-tert-butylphenol), 2,2'-ethylidenebis(4,6-di-tert-butylphenol), 2,2'-ethylidenebis(6-tert-butyl-4-isobutylphenol), 2,2'-methylenebis[6-( $\alpha$ -methylbenzyl)-4-nonylphenol], 2,2'-methylenebis[6-( $\alpha,\alpha$ -dimethylbenzyl)-4-nonylphenol], 4,4'-methylenebis(2,6-di-tert-butylphenol), 4,4'-methylenebis(6-tert-butyl-2-methylphenol), 1,1-bis(5-tert-butyl-4-hydroxy-2-methylphenyl)butane, 2,6-bis(3-tert-butyl-5-methyl-2-hydroxybenzyl)-4-methylphenol, 1,1,3-tris(5-tert-butyl-4-hydroxy-2-methylphenyl)butane, 1,1-bis(5-tert-butyl-4-hydroxy-2-methylphenyl)-3-n-dodecylmercaptobutane, ethylene glycol bis[3,3-bis(3'-tert-butyl-4'-hydroxyphenyl)butyrate], bis(3-tert-butyl-4-hydroxy-5-methylphenyl)dicyclopentadiene, bis[2-(3'-tert-butyl-2'-hydroxy-5'-methylbenzyl)-6-tert-butyl-4-methylphenyl]terephthalate, 1,1-bis-(3,5-dimethyl-2-hydroxyphenyl)butane, 2,2-bis(3,5-di-tert-butyl-4-hydroxyphenyl)propane, 2,2-bis-(5-tert-butyl-4-hydroxy-2-methylphenyl)-4-n-dodecylmercaptobutane, 1,1,5,5-tetra(5-tert-butyl-4-hydroxy-2-methylphenyl)pentane.

1.7. O-, N- and S-benzyl compounds, for example 3,5,3',5'-tetra-tert-butyl-4,4'-dihydroxydibenzyl ether, octadecyl-4-hydroxy-3,5-dimethylbenzylmercaptoacetate, tridecyl-4-hydroxy-3,5-di-tert-butylbenzylmercaptoacetate, tris(3,5-di-tert-butyl-4-hydroxybenzyl)amine, bis(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl)dithioterephthalate, bis(3,5-di-tert-butyl-4-hydroxybenzyl)sulfide, isooctyl-3,5-di-tert-butyl-4-hydroxybenzylmercaptoacetate.

1.8. Hydroxybenzylated malonates, for example dioctadecyl-2,2-bis(3,5-di-tert-butyl-2-hydroxybenzyl)malonate, di-octadecyl-2-(3-tert-butyl-4-hydroxy-5-methylbenzyl)malonate, di-dodecylmercaptoethyl-2,2-bis(3,5-di-tert-butyl-4-hydroxybenzyl)malonate, bis[4-(1,1,3,3-tetramethylbutyl)phenyl]-2,2-bis(3,5-di-tert-butyl-4-hydroxybenzyl)malonate.

1.9. Aromatic hydroxybenzyl compounds, for example 1,3,5-tris(3,5-di-tert-butyl-4-hydroxybenzyl)-2,4,6-trimethylbenzene, 1,4-bis(3,5-di-tert-butyl-4-hydroxybenzyl)-2,3,5,6-tetramethylbenzene, 2,4,6-tris(3,5-di-tert-butyl-4-hydroxybenzyl)phenol.

1.10. Triazine compounds, for example 2,4-bis(octylmercapto)-6-(3,5-di-tert-butyl-4-hydroxyanilino)-1,3,5-triazine, 2-octylmercapto-4,6-bis(3,5-di-tert-butyl-4-hydroxyanilino)-1,3,5-triazine, 2-octylmercapto-4,6-bis(3,5-di-tert-butyl-4-hydroxyphenoxy)-1,3,5-triazine, 2,4,6-tris(3,5-di-tert-butyl-4-hydroxyphenoxy)-1,2,3-triazine, 1,3,5-tris(3,5-di-tert-butyl-4-hydroxybenzyl)isocyanurate, 1,3,5-tris(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl)isocyanurate, 2,4,6-tris(3,5-di-tert-butyl-4-hydroxyphenylethyl)-1,3,5-triazine, 1,3,5-tris(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)-hexahydro-1,3,5-triazine, 1,3,5-tris(3,5-dicyclohexyl-4-hydroxybenzyl)isocyanurate.

1.11. Benzylphosphonates, for example dimethyl-2,5-di-tert-butyl-4-hydroxybenzylphosphonate, diethyl-3,5-di-tert-butyl-4-hydroxybenzylphosphonate, dioctadecyl-3,5-di-tert-butyl-4-hydroxybenzylphosphonate, dioctadecyl-5-tert-butyl-4-hydroxy-3-methylbenzylphosphonate, the calcium salt of the monoethyl ester of 3,5-di-tert-butyl-4-hydroxybenzylphosphonic acid.

1.12. Acylaminophenols, for example 4-hydroxylauranilide, 4-hydroxystearanilide, octyl N-(3,5-di-tert-butyl-4-hydroxyphenyl)carbamate.

1.13. Esters of  $\beta$ -(3,5-di-tert-butyl-4-hydroxyphenyl)propionic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, n-octanol, i-octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl)isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.

1.14. Esters of  $\beta$ -(5-tert-butyl-4-hydroxy-3-methylphenyl)propionic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, n-octanol, i-octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl)isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane; 3,9-bis[2-(3-(3-tert-

butyl-4-hydroxy-5-methylphenyl)propionyloxy]-1,1-dimethylethyl]-2,4,8,10-tetraoxaspiro[5.5]-undecane.

1.15. Esters of  $\beta$ -(3,5-dicyclohexyl-4-hydroxyphenyl)propionic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl)isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.

1.16. Esters of 3,5-di-tert-butyl-4-hydroxyphenyl acetic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl)isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.

1.17. Amides of  $\beta$ -(3,5-di-tert-butyl-4-hydroxyphenyl)propionic acid e.g. N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)hexamethylenediamide, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)trimethylenediamide, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)hydrazide, N,N'-bis[2-(3-[3,5-di-tert-butyl-4-hydroxyphenyl]propionyloxy)ethyl]oxamide (Nau-gard®XL-1, supplied by Uniroyal).

1.18. Ascorbic acid (vitamin C)

1.19. Aminic antioxidants, for example N,N'-di-isopropyl-p-phenylenediamine, N,N'-di-sec-butyl-p-phenylenediamine, N,N'-bis(1,4-dimethylpentyl)-p-phenylenediamine, N,N'-bis(1-ethyl-3-methylpentyl)-p-phenylenediamine, N,N'-bis(1-methylheptyl)-p-phenylenediamine, N,N'-dicyclohexyl-p-phenylenediamine, N,N'-diphenyl-p-phenylenediamine, N,N'-bis(2-naphthyl)-p-phenylenediamine, N-isopropyl-N'-phenyl-p-phenylenediamine, N-(1,3-dimethylbutyl)-N'-phenyl-p-phenylenediamine, N-(1-methylheptyl)-N'-phenyl-p-phenylenediamine, N-cyclohexyl-N'-phenyl-p-phenylenediamine, 4-(p-toluenesulfamoyl)diphenylamine, N,N'-dimethyl-N,N'-di-sec-butyl-p-phenylenediamine, diphenylamine, N-allyldiphenylamine, 4-isopropoxy-diphenylamine, N-phenyl-1-naphthylamine, N-(4-tert-octylphenyl)-1-naphthylamine, N-phe-

nyl-2-naphthylamine, octylated diphenylamine, for example p,p'-di-tert-octyldiphenylamine, 4-n-butylaminophenol, 4-butyrylaminophenol, 4-nonanoylaminophenol, 4-dodecanoylaminophenol, 4-octadecanoylaminophenol, bis(4-methoxyphenyl)amine, 2,6-di-tert-butyl-4-dimethylaminomethylphenol, 2,4'-diaminodiphenylmethane, 4,4'-diaminodiphenylmethane, N,N,N',N'-tetramethyl-4,4'-diaminodiphenylmethane, 1,2-bis[(2-methylphenyl)amino]ethane, 1,2-bis(phenylamino)propane, (o-tolyl)biguanide, bis[4-(1',3'-dimethylbutyl)phenyl]amine, tert-octylated N-phenyl-1-naphthylamine, a mixture of mono- and dialkylated tert-butyl/tert-octyldiphenylamines, a mixture of mono- and dialkylated nonyldiphenylamines, a mixture of mono- and dialkylated dodecyldiphenylamines, a mixture of mono- and dialkylated isopropyl/isohexyldiphenylamines, a mixture of mono- and dialkylated tert-butyldiphenylamines, 2,3-dihydro-3,3-dimethyl-4H-1,4-benzothiazine, phenothiazine, a mixture of mono- and dialkylated tert-butyl/tert-octylphenothiazines, a mixture of mono- and dialkylated tert-octylphenothiazines, N-allylphenothiazine, N,N,N',N'-tetraphenyl-1,4-diaminobut-2-ene, N,N-bis-(2,2,6,6-tetramethyl-piperid-4-yl-hexamethylenediamine, bis(2,2,6,6-tetramethylpiperid-4-yl)-sebacate, 2,2,6,6-tetramethylpiperidin-4-one, 2,2,6,6-tetramethylpiperidin-4-ol.

## 2. UV absorbers and light stabilisers

2.1. 2-(2'-Hydroxyphenyl)benzotriazoles, for example 2-(2'-hydroxy-5'-methylphenyl)benzotriazole, 2-(3',5'-di-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(5'-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(2'-hydroxy-5'-(1,1,3,3-tetramethylbutyl)phenyl)benzotriazole, 2-(3',5'-di-tert-butyl-2'-hydroxyphenyl)-5-chlorobenzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-methylphenyl)-5-chlorobenzotriazole, 2-(3'-sec-butyl-5'-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(2'-hydroxy-4'-octyloxyphenyl)benzotriazole, 2-(3',5'-di-tert-amyl-2'-hydroxyphenyl)benzotriazole, 2-(3',5'-bis(α,α-dimethylbenzyl)-2'-hydroxyphenyl)benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-octyloxycarbonylethyl)phenyl)-5-chlorobenzotriazole, 2-(3'-tert-butyl-5'-[2-(2-ethylhexyloxy)carbonylethyl]-2'-hydroxyphenyl)-5-chlorobenzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-methoxycarbonylethyl)phenyl)-5-chlorobenzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-methoxycarbonylethyl)phenyl)benzotriazole, 2-(3'-tert-butyl-5'-(2-octyloxycarbonylethyl)phenyl)benzotriazole, 2-(3'-tert-butyl-5'-[2-(2-ethylhexyloxy)carbonylethyl]-2'-hydroxyphenyl)benzotriazole, 2-(3'-dodecyl-2'-hydroxy-5'-methylphenyl)benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-isooctyloxycarbonylethyl)phenyl)benzotriazole, 2,2'-methylenebis[4-(1,1,3,3-tetramethylbutyl)-6-benzotriazole-2-yl]phenol]; the transesterification product of 2-[3'-tert-butyl-5'-(2-methoxycarbonylethyl)-2'-hydroxyphenyl]-2H-benzotriazole with polyethylene glycol

300:  $\left[ R-CH_2CH_2-COO-CH_2CH_2 \right]_2$ , where R = 3'-tert-butyl-4'-hydroxy-5'-2H-benzotriazol-2-ylphenyl, 2-[2'-hydroxy-3'-( $\alpha,\alpha$ -dimethylbenzyl)-5'-(1,1,3,3-tetramethylbutyl)phenyl]-benzotriazole; 2-[2'-hydroxy-3'-(1,1,3,3-tetramethylbutyl)-5'-( $\alpha,\alpha$ -dimethylbenzyl)phenyl]benzotriazole.

2.2. 2-Hydroxybenzophenones, for example the 4-hydroxy, 4-methoxy, 4-octyloxy, 4-decyloxy, 4-dodecyloxy, 4-benzyloxy, 4,2',4'-trihydroxy and 2'-hydroxy-4,4'-dimethoxy derivatives.

2.3. Esters of substituted and unsubstituted benzoic acids, for example 4-tert-butylphenyl salicylate, phenyl salicylate, octylphenyl salicylate, dibenzoyl resorcinol, bis(4-tert-butylbenzoyl)resorcinol, benzoyl resorcinol, 2,4-di-tert-butylphenyl 3,5-di-tert-butyl-4-hydroxybenzoate, hexadecyl 3,5-di-tert-butyl-4-hydroxybenzoate, octadecyl 3,5-di-tert-butyl-4-hydroxybenzoate, 2-methyl-4,6-di-tert-butylphenyl 3,5-di-tert-butyl-4-hydroxybenzoate.

2.4. Acrylates, for example ethyl  $\alpha$ -cyano- $\beta,\beta$ -diphenylacrylate, isooctyl  $\alpha$ -cyano- $\beta,\beta$ -diphenylacrylate, methyl  $\alpha$ -carbomethoxycinnamate, methyl  $\alpha$ -cyano- $\beta$ -methyl-p-methoxycinnamate, butyl  $\alpha$ -cyano- $\beta$ -methyl-p-methoxycinnamate, methyl  $\alpha$ -carbomethoxy-p-methoxycinnamate and N-( $\beta$ -carbomethoxy- $\beta$ -cyanovinyl)-2-methylindoline.

2.5. Nickel compounds, for example nickel complexes of 2,2'-thiobis[4-(1,1,3,3-tetramethylbutyl)phenol], such as the 1:1 or 1:2 complex, with or without additional ligands such as n-butylamine, triethanolamine or N-cyclonexyldiethanolamine, nickel dibutyldithiocarbamate, nickel salts of the monoalkyl esters, e.g. the methyl or ethyl ester, of 4-hydroxy-3,5-di-tert-butylbenzylphosphonic acid, nickel complexes of ketoximes, e.g. of 2-hydroxy-4-methylphenylundecylketoxime, nickel complexes of 1-phenyl-4-lauroyl-5-hydroxypyrazole, with or without additional ligands.

2.6. Sterically hindered amines, for example bis(2,2,6,6-tetramethyl-4-piperidyl)sebacate, bis(2,2,6,6-tetramethyl-4-piperidyl)succinate, bis(1,2,2,6,6-pentamethyl-4-piperidyl)sebacate, bis(1-octyloxy-2,2,6,6-tetramethyl-4-piperidyl)sebacate, bis(1,2,2,6,6-pentamethyl-4-piperidyl) n-butyl-3,5-di-tert-butyl-4-hydroxybenzylmalonate, the condensate of 1-(2-hydroxyethyl)-2,2,6,6-tetramethyl-4-hydroxypiperidine and succinic acid, linear or cyclic condensates of N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-tert-octylamino-2,6-di-

chloro-1,3,5-triazine, tris(2,2,6,6-tetramethyl-4-piperidyl)nitrilotriacetate, tetrakis(2,2,6,6-tetramethyl-4-piperidyl)-1,2,3,4-butanetetracarboxylate, 1,1'-(1,2-ethanediyl)-bis(3,3,5,5-tetramethylpiperazinone), 4-benzoyl-2,2,6,6-tetramethylpiperidine, 4-stearyloxy-2,2,6,6-tetramethylpiperidine, bis(1,2,2,6,6-pentamethylpiperidyl)-2-n-butyl-2-(2-hydroxy-3,5-di-tert-butylbenzyl)-malonate, 3-n-octyl-7,7,9,9-tetramethyl-1,3,8-triazaspiro[4.5]decane-2,4-dione, bis(1-octyloxy-2,2,6,6-tetramethylpiperidyl)sebacate, bis(1-octyloxy-2,2,6,6-tetramethylpiperidyl)succinate, linear or cyclic condensates of N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-morpholino-2,6-dichloro-1,3,5-triazine, the condensate of 2-chloro-4,6-bis(4-n-butylamino-2,2,6,6-tetramethylpiperidyl)-1,3,5-triazine and 1,2-bis(3-aminopropylamino)ethane, the condensate of 2-chloro-4,6-di-(4-n-butylamino-1,2,2,6,6-pentamethylpiperidyl)-1,3,5-triazine and 1,2-bis(3-aminopropylamino)ethane, 8-acetyl-3-dodecyl-7,7,9,9-tetramethyl-1,3,8-triazaspiro[4.5]decane-2,4-dione, 3-dodecyl-1-(2,2,6,6-tetramethyl-4-piperidyl)pyrrolidine-2,5-dione, 3-dodecyl-1-(1,2,2,6,6-pentamethyl-4-piperidyl)pyrrolidine-2,5-dione, 5-(2-ethylhexanoyl)-oxymethyl-3,3,5-trimethyl-2-morpholinone, 1-(2-hydroxy-2-methylpropoxy)-4-octadecanoyloxy-2,2,6,6-tetramethylpiperidine, 1,3,5-tris(N-cyclohexyl-N-(2,2,6,6-tetramethylpiperazin-3-on-4-yl)amino)-s-triazine, 1,3,5-tris(N-cyclohexyl-N-(1,2,2,6,6-pentamethylpiperazin-3-on-4-yl)amino)-s-triazine, the reaction product of 2,4-bis[(1-cyclohexyloxy-2,2,6,6-piperidin-4-yl)butylamino]-6-chloro-s-triazine with N,N'-bis(3-aminopropyl)ethylenediamine), a mixture of 4-hexadecyloxy- and 4-stearyloxy-2,2,6,6-tetramethylpiperidine, a condensate of N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-cyclohexylamino-2,6-dichloro-1,3,5-triazine, a condensate of 1,2-bis(3-aminopropylamino)ethane and 2,4,6-trichloro-1,3,5-triazine as well as 4-butylamino-2,2,6,6-tetramethylpiperidine (CAS Reg. No. [136504-96-6]); a condensate of 1,6-hexanediamine and 2,4,6-trichloro-1,3,5-triazine as well as N,N-dibutylamine and 4-butylamino-2,2,6,6-tetramethylpiperidine (CAS Reg. No. [192268-64-7]); N-(2,2,6,6-tetramethyl-4-piperidyl)-n-dodecylsuccinimide; N-(1,2,2,6,6-pentamethyl-4-piperidyl)-n-dodecylsuccinimide; 2-undecyl-7,7,9,9-tetramethyl-1-oxa-3,8-diaza-4-oxo-spiro[4.5]decane; 5-(2-ethylhexanoyl)oxymethyl-3,3,5-trimethyl-2-morpholinone; a reaction product of 7,7,9,9-tetramethyl-2-cycloundecyl-1-oxa-3,8-diaza-4-oxospiro[4.5]decane and epichlorohydrin, 1,1-bis(1,2,2,6,6-pentamethyl-4-piperidyl)oxycarbonyl-2-(4-methoxyphenyl)ethene, N,N'-bis-formyl-N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine, a diester of 4-methoxymethylenemalononic acid with 1,2,2,6,6-pentamethyl-4-hydroxypiperidine, poly[methylpropyl-3-oxy-4-(2,2,6,6-tetramethyl-4-piperidyl)]siloxane, a reaction product of



maleic acid anhydride- $\alpha$ -olefin copolymer with 2,2,6,6-tetramethyl-4-aminopiperidine or 1,2,2,6,6-pentamethyl-4-aminopiperidine.

2.7. Oxamides, for example 4,4'-dioctyloxyoxanilide, 2,2'-diethoxyoxanilide, 2,2'-dioctyloxy-5,5'-di-tert-butoxanilide, 2,2'-didodecyloxy-5,5'-di-tert-butoxanilide, 2-ethoxy-2'-ethyloxanilide, N,N'-bis(3-dimethylaminopropyl)oxamide, 2-ethoxy-5-tert-butyl-2'-ethoxanilide and its mixture with 2-ethoxy-2'-ethyl-5,4'-di-tert-butoxanilide, mixtures of o- and p-methoxy-disubstituted oxanilides and mixtures of o- and p-ethoxy-disubstituted oxanilides.

2.8. 2-(2-Hydroxyphenyl)-1,3,5-triazines, for example 2,4,6-tris(2-hydroxy-4-octyloxyphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2,4-dihydroxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2,4-bis(2-hydroxy-4-propyloxyphenyl)-6-(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis(4-methylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-dodecyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-tridecyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-butyloxypropoxy)phenyl]-4,6-bis(2,4-dimethyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-octyloxypropyloxy)phenyl]-4,6-bis(2,4-dimethyl)-1,3,5-triazine, 2-[4-(dodecyloxy/tridecyloxy-2-hydroxypropoxy)-2-hydroxyphenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-dodecyloxypropoxy)phenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-hexyloxy)phenyl-4,6-diphenyl-1,3,5-triazine, 2-(2-hydroxy-4-methoxyphenyl)-4,6-diphenyl-1,3,5-triazine, 2,4,6-tris[2-hydroxy-4-(3-butoxy-2-hydroxypropoxy)phenyl]-1,3,5-triazine, 2-(2-hydroxyphenyl)-4-(4-methoxyphenyl)-6-phenyl-1,3,5-triazine, 2-[2-hydroxy-4-[3-(2-ethylhexyl-1-oxy)-2-hydroxypropyloxy]phenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine.




3. Metal deactivators, for example N,N'-diphenyloxamide, N-salicylal-N'-salicyloyl hydrazine, N,N'-bis(salicyloyl)hydrazine, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)hydrazine, 3-salicyloylamino-1,2,4-triazole, bis(benzylidene)oxalyl dihydrazide, oxanilide, isophthaloyl dihydrazide, sebacoyl bisphenylhydrazide, N,N'-diacetyl adipoyl dihydrazide, N,N'-bis(salicyloyl)oxalyl dihydrazide, N,N'-bis(salicyloyl)thiopropionyl dihydrazide.




4. Phosphites and phosphonites, for example triphenyl phosphite, diphenylalkyl phosphites, phenyldialkyl phosphites, tris(nonylphenyl) phosphite, trilauryl phosphite, trioctadecyl phosphite, distearyl/pentaerythritol diphosphite, tris(2,4-di-tert-butylphenyl) phosphite, dilsodecyl

pentaerythritol diphosphite, bis(2,4-di-tert-butylphenyl)pentaerythritol diphosphite, bis(2,4-dicumylphenyl)pentaerythritol diphosphite, bis(2,6-di-tert-butyl-4-methylphenyl)pentaerythritol diphosphite, diisodecylpentaerythritol diphosphite, bis(2,4-di-tert-butyl-6-methylphenyl)pentaerythritol diphosphite, bis(2,4,6-tris(tert-butylphenyl)pentaerythritol diphosphite, tristearyl sorbitol triphosphite, tetrakis(2,4-di-tert-butylphenyl) 4,4'-biphenylene diphosphonite, 6-isoctyloxy-2,4,8,10-tetra-tert-butyl-12-methyl-dibenz[d,g]-1,3,2-dioxaphosphocin, bis(2,4-di-tert-butyl-6-methylphenyl)methyl phosphite, bis(2,4-di-tert-butyl-6-methylphenyl)ethyl phosphite, 6-fluoro-2,4,8,10-tetra-tert-butyl-12-methyl-dibenz[d,g]-1,3,2-dioxaphosphocin, 2,2',2''-nitrilo-[triethyltris(3,3',5,5'-tetra-tert-butyl-1,1'-biphenyl-2,2'-diyl)phosphite], 2-ethylhexyl(3,3',5,5'-tetra-tert-butyl-1,1'-biphenyl-2,2'-diyl)phosphite, 5-butyl-5-ethyl-2-(2,4,6-tri-tert-butylphenoxy)-1,3,2-dioxaphosphirane.

The following phosphites are especially preferred:

Tris(2,4-di-tert-butylphenyl) phosphite (Irgafos®168, Ciba-Geigy), tris(nonylphenyl) phosphite,





5. Hydroxylamines, for example N,N-dibenzylhydroxylamine, N,N-diethylhydroxylamine, N,N-dioctylhydroxylamine, N,N-dilaurylhydroxylamine, N,N-ditetradecylhydroxylamine, N,N-dihexadecylhydroxylamine, N,N-dioctadecylhydroxylamine, N-hexadecyl-N-octadecylhydroxylamine, N-heptadecyl-N-octadecylhydroxylamine, N,N-dialkylhydroxylamine derived from hydrogenated tallow amine.

6. Nitrones, for example N-benzyl-alpha-phenylnitrone, N-ethyl-alpha-methylnitrone, N-octyl-alpha-heptylnitrone, N-lauryl-alpha-undecylnitrone, N-tetradecyl-alpha-tridecyl-nitrone, N-hexadecyl-alpha-pentadecylnitrone, N-octadecyl-alpha-heptadecylnitrone, N-hexadecyl-alpha-heptadecylnitrone, N-octadecyl-alpha-pentadecylnitrone, N-heptadecyl-alpha-heptadecylnitrone, N-octadecyl-alpha-hexadecylnitrone, nitrone derived from N,N-dialkylhydroxylamine derived from hydrogenated tallow amine.

7. Thiosynergists, for example dilauryl thiodipropionate or distearyl thiodipropionate.

8. Peroxide scavengers, for example esters of  $\beta$ -thiodipropionic acid, for example the lauryl, stearyl, myristyl or tridecyl esters, mercaptobenzimidazole or the zinc salt of 2-mercaptobenzimidazole, zinc dibutyldithiocarbamate, dioctadecyl disulfide, pentaerythritol tetrakis( $\beta$ -dodecylmercapto)propionate.

9. Polyamide stabilisers, for example copper salts in combination with iodides and/or phosphorus compounds and salts of divalent manganese.

10. Basic co-stabilisers, for example melamine, polyvinylpyrrolidone, dicyandiamide, triallyl cyanurate, urea derivatives, hydrazine derivatives, amines, polyamides, polyurethanes, alkali metal salts and alkaline earth metal salts of higher fatty acids, for example calcium stearate, zinc stearate, magnesium behenate, magnesium stearate, sodium ricinoleate and potassium palmitate, antimony pyrocatecholate or zinc pyrocatecholate.

11. Nucleating agents, for example inorganic substances, such as talcum, metal oxides, such as titanium dioxide or magnesium oxide, phosphates, carbonates or sulfates of, preferably, alkaline earth metals; organic compounds, such as mono- or polycarboxylic acids and the salts thereof, e.g. 4-tert-butylbenzoic acid, adipic acid, diphenylacetic acid, sodium succinate or sodium benzoate; polymeric compounds, such as ionic copolymers (ionomers). Especially preferred are 1,3:2,4-bis(3',4'-dimethylbenzylidene)sorbitol, 1,3:2,4-di(paramethyl-dibenzylidene)sorbitol, and 1,3:2,4-di(benzylidene)sorbitol.

12. Fillers and reinforcing agents, for example calcium carbonate, silicates, glass fibres, glass beads, asbestos, talc, kaolin, mica, barium sulfate, metal oxides and hydroxides, carbon black, graphite, wood flour and flours or fibers of other natural products, synthetic fibers.

13. Other additives, for example plasticisers, lubricants, emulsifiers, pigments, rheology additives, catalysts, flow-control agents, optical brighteners, flameproofing agents, antistatic agents and blowing agents.

14. Benzofuranones and indolinones, for example those disclosed in U.S. 4,325,863; U.S. 4,338,244; U.S. 5,175,312; U.S. 5,216,052; U.S. 5,252,643; DE-A-4316611; DE-A-4316622; DE-A-4316876; EP-A-0589839 or EP-A-0591102 or 3-[4-(2-acetoxyethoxy)-phenyl]-5,7-di-tert-butyl-benzofuran-2-one, 5,7-di-tert-butyl-3-[4-(2-stearoyloxyethoxy)ph-

nyl]benzofuran-2-one, 3,3'-bis[5,7-di-tert-butyl-3-(4-[2-hydroxyethoxy]phenyl)benzofuran-2-one], 5,7-di-tert-butyl-3-(4-ethoxyphenyl)benzofuran-2-one, 3-(4-acetoxy-3,5-dimethylphenyl)-5,7-di-tert-butyl-benzofuran-2-one, 3-(3,5-dimethyl-4-pivaloyloxyphenyl)-5,7-di-tert-butyl-benzofuran-2-one, 3-(3,4-dimethylphenyl)-5,7-di-tert-butyl-benzofuran-2-one, 3-(2,3-dimethylphenyl)-5,7-di-tert-butyl-benzofuran-2-one.

Preferred compositions of the invention comprise, as other additives, one or more components selected from the group consisting of pigments, dyes, fillers, levelling assistants, dispersants, plasticizers, vulcanization activators, vulcanization accelerators, vulcanizers, charge control agents, adhesion promoters, light stabilizers or antioxidants, such as phenolic antioxidants (items 1.1 to 1.18 in the list) or aminic antioxidants (item 1.19 in the list), organic phosphites or phosphonites (item 4 in the list) and/or thiosynergists (item 7 in the list).

An example of the concentrations at which these other additives are added is from 0.01 to 10%, based on the total weight of the elastomer to be stabilized.

Component b), and also, if desired, other additives are incorporated into the elastomer by known methods, for example during mixing in internal mixers with rams (Banbury), on mixing rolls or in mixing extruders, prior to or during shaping or vulcanization, or else by applying dissolved or dispersed component b) to the elastomer, if desired with subsequent removal of the solvent by evaporation. When added to the elastomer to be stabilized, component b) and, if desired, other additives may also be in the form of a masterbatch comprising these, for example at a concentration of from 2.5 to 25% by weight.

Component b) and, if desired, other additives may also be added prior to or during the polymerization of synthetic elastomers or prior to crosslinking, i.e. advantageously, if desired, as a first-level stabilizer in the crude rubber, which may also comprise other components, such as carbon black as filler and/or extender oils.

The compounds of the formula I are bonded chemically (grafted) to polymer chains under processing conditions (compounding, mixing, vulcanization, etc.). The compounds of the formula I are resistant to extraction, i.e. they continue to offer good protection after the substrate is subjected to intensive extraction. The loss of compounds of the formula I from the elastomer via migration or extraction is extremely slight. The subject of the invention

therefore comprises a method of grafting a compound of formula I onto a polymer, which comprises heating, preferably in a processing apparatus for polymers, a mixture of polymer and at least one compound of formula I above the softening point of the polymer and allowing them to react with one another. Preferred temperature range for grafting is 120 – 200°C, for example 140 – 180°C, especially 150 - 170°C,

The elastomers stabilized with the compounds of the formula I also show markedly improved and desirable gloss. This means that the surface gloss of the elastomer stabilized according to the invention, after exposure to ozone, is significantly higher than that of an unstabilized elastomer or of an elastomer stabilized in accordance with the prior art. As further advantage, the use of present compounds of formula I brings about significantly lowered or non-existent contact discoloration (staining).

Component b) and, if desired, other additives may be in pure form or encapsulated in waxes, in oils or in polymers when they are incorporated into the elastomer to be stabilized.

Component b) and, if desired, other additives may also be sprayed onto the elastomer to be stabilized. They are capable of diluting other additives (e.g. the conventional additives given above) or melts of these, and they may therefore also be sprayed together with these additives onto the elastomer to be stabilized.

The resultant stabilized elastomers may be used in a wide variety of forms, e.g. ribbons, moulding compositions, profiles, conveyor belts or tyres (pneumatic).

The present invention further provides a process for stabilizing elastomers to prevent oxidative, thermal, dynamic, light-induced and/or ozone-induced degradation, which comprises incorporating into these or applying to these at least one component b).

The present invention further provides a process for preventing contact discoloration of substrates coming into contact with elastomers, which comprises incorporating into the elastomers, or applying to these, at least one component b).


A further embodiment of the present invention is the use of component b) as stabilizers for elastomers to prevent oxidative, thermal, dynamic, light-induced and/or ozone-induced degradation.

A further embodiment of the present invention is the use of component b) as stabilizers for elastomers to prevent contact discoloration of substrates coming into contact with elastomers.

The preferred compounds of the formula I [component b)] for the processes and uses listed above are the same as those for the compositions of the invention.

The examples below further illustrate the invention. Data in parts or percentages are based on weight. Room temperature stands for a temperature in the range 20-25°C. MS(Cl) denotes mass spectrometry (chemical ionization).


Example 1: Preparation of the compound



The starting thioether is obtained according to example 3 of WO 02/42262.

4.7 g (0.01 mol) of this thioether and 2 g (0.018 mol) of urea-H<sub>2</sub>O<sub>2</sub>-adduct (30 % H<sub>2</sub>O<sub>2</sub>) in 8 ml of ethanol are stirred for 6 hours at 40°C. After removal of the excess of hydrogen peroxide by washing of the organic phase with a solution of sodiumpyrosulfate (Na<sub>2</sub>S<sub>2</sub>O<sub>5</sub>), the solvent is removed by distillation. The title sulfoxide is obtained as a brown resin (yield 100 %). MS(Cl): 485 (MH<sup>+</sup>).


Example 2: Preparation of the compound



Following the method described in examples 1-15 of WO 02/42262, 3.0 mmol of N'-(1,3-dimethylbutyl)-N'-phenyl-p-quinone diimine in 25 ml of ethanol are treated at 20°C with 3.0

mmol of tert.-dodecylmercaptan with stirring. Subsequent oxidation and workup as described in example 1 yields the title product (69 % of theory) as a brown oil, MS(Cl): 485(MH<sup>+</sup>).

**Example 3: Preparation of the compound**



Following the method described in example 1-15 of WO 02/42262, 3.0 mmol of N'-(1,3-dimethylbutyl)-N-phenyl-p-quinone diimine are reacted with the equimolar amount of the mercaptan HS-CH<sub>2</sub>CH<sub>2</sub>COO-i-octyl. Subsequent oxidation and workup as described in example 1 yields the title product (95 % of theory) as a brown oil, MS(Cl): 501(MH<sup>+</sup>).

**Example 4: Stabilization of black vulcanizate.**

40.0 parts by weight of Cariflex® 1220 [polybutadiene, SHELL] are processed on mixing rolls at 60°C with 60.0 parts by weight of natural rubber and 55.0 parts by weight of carbon black (N 330), 6.0 parts by weight of Ingralene 450 (RTM) [extender oil], 5.0 parts by weight of zinc oxide [vulcanization activator], 2.0 parts by weight of stearic acid [vulcanization activator], 0.2 parts by weight of IRGANOX 1520 (RTM) [processing stabilizer, Ciba Specialty Chemicals], 2.0 parts by weight of sulfur [vulcanizer], 0.6 part by weight of Vulkacit MOZ (RTM) [vulcanization accelerator, BAYER] and 2.0 parts by weight of the stabilizer to be tested in accordance with Table 4, to give a homogeneous mixture, the vulcanization system [sulfur and Vulkacit MOZ (RTM)] not being added until the end of the mixing process. The mixture is vulcanized in electrical heating presses at 150°C to T95 on the rheometer curves, to give elastomer sheets of 2 mm thickness, 21 cm length and 8.0 cm width. Sections of the 2 mm rubber sheets are placed on a white cardboard underlay and stored in a circulating-air cabinet at 50°C for 5 days. The contact surface or its margin is then evaluated visually for contact discoloration (staining): 0 = no discoloration (or the discoloration of the reference in which no AO is present) and 5 = greatest degree of discoloration. The slighter the contact discoloration, the better the stabilization. The results are given in Table 4.




Table 4:

Example	Stabilizer (compound)	Contact discoloration - visual
4a <sup>a)</sup>	—	
4b <sup>b)</sup>	Example 1	
4c <sup>b)</sup>	Example 2	
4d <sup>b)</sup>	Example 3	
4e <sup>a)</sup>	Vulkanox 4020 <sup>c)</sup>	

a) Comparative example


b) Inventive example

c) Vulkanox 4020 (RTM) [Bayer] is 4-[1,3-dimethylbutyl]aminodiphenylamine of the formula A



What is claimed is:

1. A compound of the formula I



wherein

$R_1$  is  $C_1$ - $C_{18}$ alkyl,  $C_5$ - $C_{12}$ -cycloalkyl, phenyl, benzyl, or allyl;

$n$  is 1 or 2;

if  $n$  is 1,  $R_2$  is  $C_4$ - $C_{18}$ alkyl,  $C_5$ - $C_{12}$ -cycloalkyl, aryl or heteroaryl, benzyl, allyl,  $(CH_2)_mCOOR_3$ , or is  $(CH_2)_mCN$ ;

if  $n$  is 2,  $R_2$  is  $-S-(CH_2)_p-S$  or  $-S-(CH_2)_2-[O-(CH_2)_2]_m-S-$

$R_3$  is  $C_1$ - $C_{18}$ alkyl, benzyl, allyl;

$m$  is 1 or 2; and

$p$  is a number from 2 to 12.

2. Compound of formula I according to claim 1 wherein

$R_1$  is  $C_2$ - $C_8$ alkyl, cyclohexyl, phenyl, benzyl, or allyl,

if  $n$  is 1,  $R_2$  is  $C_4$ - $C_{18}$ alkyl, cyclohexyl, phenyl,  $(CH_2)_2COOR_3$ , or is  $(CH_2)_2CN$ ;

if  $n$  is 2,  $R_2$  is  $-S-(CH_2)_p-S$  or  $-S-(CH_2)_2-[O-(CH_2)_2]_m-S-$ ;

$R_3$  is  $C_1$ - $C_{18}$ alkyl; and


$p$  is a number from 2 to 6.

3. A composition comprising

a) a naturally occurring or synthetic elastomer susceptible to oxidative, thermal, dynamic, light-induced and/or ozone-induced degradation, and

b) as stabilizer, at least one compound of the formula I according to claim 1, especially in an amount from 0.05 to 10%, based on the weight of component a).

4. A composition according to claim 3, in which component a) is a natural or synthetic rubber or a vulcanizate prepared therefrom.
5. A composition according to claim 4, in which component a) is a polydiene vulcanizate, a halogen-containing polydiene vulcanizate, a polydiene copolymer vulcanizate or an ethylene-propylene terpolymer vulcanizate.
6. A composition according to claim 3, further comprising one or more components selected from the group consisting of pigments, dyes, fillers, levelling assistants, dispersants, plasticizers, vulcanization activators, vulcanization accelerators, vulcanizers, charge control agents, adhesion promoters, antioxidants, flame retardants, UV absorbers and light stabilizers, especially phenolic antioxidants, aminic antioxidants, organic phosphites or phosphonites and/or thio-synergists.
7. A thioether of formula II'



wherein n is 1 or 2,

R<sub>1</sub> is as defined for formula I and

R<sub>2</sub>, if n is 1, is t-nonyl or t-dodecyl or (CH<sub>2</sub>)<sub>2</sub>COOR<sub>3</sub> or (CH<sub>2</sub>)<sub>2</sub>CN, where R<sub>3</sub> is C<sub>1</sub>-C<sub>16</sub>alkyl, especially i-octyl, i-tridecyl, n-dodecyl, stearyl; or

R<sub>2</sub>, if n is 2, is -S-(CH<sub>2</sub>)<sub>p</sub>-S- with p ranging from 2 to 6.


8. A method of grafting a compound of formula I according to claim 1 onto an elastomer, which comprises heating a mixture of elastomer and at least one compound of formula I according to claim 1 above the softening point of the elastomer and allowing them to react with one another.

**9.** Use of a compound of formula I according to claim 1 as a stabiliser for an elastomer to prevent oxidative, thermal, dynamic, light-induced and/or ozone-induced degradation and/or contact discoloration of substrates coming into contact with the elastomer.

**10.** A process for stabilizing an elastomer to prevent oxidative, thermal, dynamic, light-induced and/or ozone-induced degradation and preventing contact discoloration of substrates coming into contact with the elastomer, which process comprises incorporating into these or applying to these at least one compound of formula I according to claim 1.

Abstract

Compounds of the formula I



wherein

R<sub>1</sub> is C<sub>1</sub>-C<sub>18</sub>alkyl, C<sub>5</sub>-C<sub>12</sub>-cycloalkyl, phenyl, benzyl, or allyl;

n is 1 or 2;

if n is 1, R<sub>2</sub> is C<sub>4</sub>-C<sub>18</sub>alkyl, C<sub>5</sub>-C<sub>12</sub>-cycloalkyl, aryl or heteroaryl, benzyl, allyl, (CH<sub>2</sub>)<sub>m</sub>COOR<sub>3</sub>, or is (CH<sub>2</sub>)<sub>m</sub>CN;

if n is 2, R<sub>2</sub> is -S-(CH<sub>2</sub>)<sub>p</sub>-S

or

-S-(CH<sub>2</sub>)<sub>2</sub>-[O-(CH<sub>2</sub>)<sub>2</sub>]<sub>m</sub>-S-

R<sub>3</sub> is C<sub>1</sub>-C<sub>18</sub>alkyl, benzyl, allyl;

m is 1 or 2; and

p is a number from 2 to 12;

are suitable as a stabiliser for an elastomer to prevent oxidative, thermal, dynamic, light-induced and/or ozone-induced degradation. They are also suitable as stabilizers for elastomers to prevent contact discoloration of substrates coming into contact with elastomers.

PCT Application

**EP0310836**



**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**